


AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. **(Currently Amended)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, comprising



(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



wherein R¹ and R² each are a substituted or unsubstituted monovalent hydrocarbon radical, wherein the diorganopolysiloxane further contains alkenyl radicals in amount of 0.02 to 0.5 mol% based on the total of R¹ and R², and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of R³₃SiO_{1/2} units and SiO_{4/2} units in a molar ratio of R³₃SiO_{1/2} units to SiO_{4/2} units of from 0.5 to 1.5, wherein R³ is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of: ~~a silane or siloxane compound having a silicon atom bonded alkoxy radical and an organic radical or atom selected from the group consisting of an~~

~~alkenyl radical and a silicon atom-bonded hydrogen atom, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof, and~~



(C) a crosslinking agent comprising (a) an organohydrogenpolysiloxane having at least two silicon atom-bonded hydrogen atoms in a molecule, in an amount to give 0.2 to 30 mol of silicon atom-bonded hydrogen atoms per mol of alkenyl radicals in components (A) and (B), and (b) a catalytic amount of a platinum base catalyst.


2-3. (Canceled)

4. (Previously Presented) A silicone adhesive film prepared by forming the adhesive of claim 1 into a film shape.

5. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 1 into a film shape, followed by crosslinking and curing.



6. **(Currently Amended)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, said silicon adhesive comprising:

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



wherein R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, wherein the diorganopolysiloxane further contains alkenyl radicals in amount of 0.02 to 0.5 mol% based on the total of R^1 and R^2 , and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of $\text{R}^3_3\text{SiO}_{1/2}$ units and $\text{SiO}_{4/2}$ units in a molar ratio of $\text{R}^3_3\text{SiO}_{1/2}$ units to $\text{SiO}_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of: ~~a silane or siloxane compound having a silicon atom-bonded alkoxy radical and an alkenyl group or an epoxy radical, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof, and~~



, and

(C) (a) an organohydrogenpolysiloxane having at least two silicon atom-bonded hydrogen atoms in a molecule, in an amount to give 0.2 to 30 mol of silicon atom-bonded hydrogen atoms per mol of alkenyl radicals in components (A) and (B), and (b) a catalytic amount of a platinum base catalyst.

7. **(Previously Presented)** A silicone adhesive film prepared by forming the adhesive of claim 6 into a film shape.

8. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 6 into a film shape, followed by crosslinking and curing.

9-10. **(Canceled)**

11. (Currently Amended) A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, comprising:

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):










wherein R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of $\text{R}^3_3\text{SiO}_{1/2}$ units and $\text{SiO}_{4/2}$ units in a molar ratio of $\text{R}^3_3\text{SiO}_{1/2}$ units to $\text{SiO}_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of: ~~a silane or siloxane compound selected from the group consisting of the following compounds:~~



~~glycidoxypentyltrimethoxysilane;~~

~~glycidoxypentyltriethoxysilane;~~





wherein p and r each are an integer of 0 to 50, q, s and t each are an integer of 1 to 50,



(C) a crosslinking agent in the form of an organic peroxide.

12-13. **(Canceled)**

14. **(Previously Presented)** A silicone adhesive film prepared by forming the adhesive of claim 11 into a film shape.

15. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 11 into a film shape, followed by crosslinking and curing.

16-19. **(Canceled)**